

WHAT IS CLAIMED IS:

1. A joint to be adhered to nylon resin moldings using a solvent adhesive, in which a material for the joint comprises a copolymerized nylon.

2. A joint to be adhered to nylon resin moldings using a solvent adhesive, in which a material for the joint comprises a composition comprising a copolymerized nylon and at least one of a nucleating agent and a lubricant.

3. A joint to be adhered to nylon resin moldings using a solvent adhesive, in which a material for the joint comprises a composition comprising a copolymerized nylon blend and at least one of a nucleating agent and a lubricant.

4. The joint to be adhered to nylon resin moldings as claimed in one of claims 1 to 3, wherein the copolymerized nylon comprises two or more kinds of units derived from lactams containing 6 to 12 carbon atoms, aminocarboxylic acids containing 6 to 12 carbon atoms, and a combination of a dicarboxylic acid containing 3 to 22 carbon atoms and a diamine containing 2 to 20 carbon atoms.

5. The joint to be adhered to nylon resin moldings as claimed in claim 3, wherein the copolymerized nylon blend is a blend of a copolymerized nylon and a nylon selected from the group consisting of nylon 6, nylon 11, nylon 12, nylon 6,6, nylon 6,10 and nylon 6,12.

6. The joint to be adhered to nylon resin moldings as claimed in claim 2 or 3, wherein the nucleating agent is talc, with its content being 0.1 to 5 parts by weight per 100 parts by weight of the resin component.

7. The joint to be adhered to nylon resin moldings as claimed in claim 2 or 3, wherein the lubricant is a metal soap, with its content being 0.05 to 5 parts by weight per 100 parts by weight of the resin component.

8. The joint to be adhered to nylon resin moldings as claimed in one of claims 1 to 3, wherein the copolymerized nylon comprises 5 to 95% by weight of nylon-12 component, based on the total weight of the copolymerized nylon.

9. The joint to be adhered to nylon resin moldings as claimed in claim 3, wherein the copolymerized nylon blend comprises 50 to 90% by weight of the copolymerized nylon and 50 to 10% by weight of nylon 12, based on the total weight of the copolymerized nylon blend.

10. The joint to be adhered to nylon resin moldings as claimed in one of claims 1 to 3, which has a dissimilar material molded structure in such a manner that a material for the joint claimed in one of claims 1 to 3 constitutes at least a portion of the joint to be adhered to the nylon resin moldings.

11. A method for adhering nylon resin moldings, which comprises adhering the nylon resin moldings to a joint comprising (i) a copolymerized nylon or (ii) a

composition comprising a copolymerized nylon or a copolymerized nylon blend and at least one of a nucleating agent and a lubricant using a solvent adhesive.

12. The method for adhering nylon resin moldings as claimed in claim 11, wherein the solvent adhesive comprises at least one component of a phenolic compound and a fluoroalcoholic compound.

13. The method for adhering nylon resin moldings as claimed in claim 11 or 12, wherein the solvent adhesive comprises a copolymerized nylon.

14. A solvent adhesive for nylon resin moldings, which comprises a solvent and a copolymerized nylon.

15. The solvent adhesive for nylon resin moldings as claimed in claim 14, which comprises 0.5 to 20% by weight, based on the total weight of the solvent adhesive, of a copolymerized nylon comprising two or more kinds of units derived from lactams containing 6 to 12 carbon atoms, aminocarboxylic acids containing 6 to 12 carbon atoms, and a combination of a dicarboxylic acid containing 3 to 22 carbon atoms and a diamine containing 2 to 20 carbon atoms.

16. The solvent adhesive for nylon resin moldings as claimed in claim 15, wherein the copolymerized nylon comprises 5 to 95% by weight of nylon 12 component, based on the total weight of the copolymerized nylon.

17. The solvent adhesive for nylon resin moldings as claimed in one of claims 14 to 16, wherein the solvent

comprises at least one of phenolic compounds and fluoroalcoholic compounds.

18. An adhesion structure of nylon resin, wherein a material comprising a copolymerized nylon is adhered to a material comprising other nylon resin using a solvent adhesive.

19. An adhesion structure of nylon resin, wherein a material comprising a composition comprising a copolymerized nylon or a copolymerized nylon blend and at least one of a nucleating agent and a lubricant is adhered to a material comprising other nylon resin using a solvent adhesive.

20. The adhesion structure of nylon resin as claimed in claim 18 or 19, wherein the solvent adhesive comprises a copolymerized nylon.